



TECHNICAL DATA SHEET

UNICOLOUR 900 2K BASECOAT

MIXED COLOURS

PRODUCT DESCRIPTION

This product is the basecoat part of a high performance 2 Pack Clear Over Base (C.O.B) system designed in Australia for the Australian Market. All colours have high opacity and excellent flow.

PRODUCT AND ADDITIVES

- Concept Unicolour 900 2K Basecoat Mixed Colour
- Concept Basecoat Reducer Range




SUITABLE SUBSTRATES

- Concept HS 2K Primer (High Build)
- Sound existing surfaces, except for weak surfaces such as nitrocellulose or enamels.

MIXING RATIO




- 1 part Concept Unicolour 900 2K Basecoat colour by volume.
- 50 – 80% Concept Basecoat Reducer by volume.

SPRAY GUN AND PRESSURE

SPRAY GUN & PRESSURE:	<ul style="list-style-type: none">• 1.2 - 1.4mm through suction feed.• Pressure is 350 – 450 kPa (Gravity feed is slightly higher pressure).	
-----------------------	---	---

APPLICATION

- All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.
- Apply two to three even coats.

SPRAYING VISCOSITY:	<ul style="list-style-type: none"> • 17 – 18 seconds B4 cup at 25°C. 	 17-18 SECONDS
FLASH-OFF TIME:	<ul style="list-style-type: none"> • 5 – 10 minutes between coats at 25°C. 	
DRYING:	<ul style="list-style-type: none"> • 30 – 40 minutes at 25°C for a Dry Film Thickness of 20 – 25 Micron. 	

TECHNICAL INFORMATION

COLOUR:	Large Range of Colour Formulations Available
COVERAGE:	8 m ² /L @ 25 Micron Dry Film Thickness.
PACKAGING:	1LT, 4LT, 20LT
ITEM CODE:	A12/900
SHELF LIFE:	12 Months

The above information is reliable and accurate to the best of our knowledge at the time of preparation. Any recommendations or suggestions made are without warranty or guarantee. Users assume all responsibility since the conditions of use are beyond our control.

REVISED: 15 February 2006

REPLACES ISSUE: