



# TECHNICAL DATA SHEET

## BASECOAT BLEND CONTROL

### PRODUCT DESCRIPTION

This product has been designed to control blend outs in conjunction with Concept Unicolour 900 2K Basecoat System and Concept No Mix System. It fills scratches caused by light sanding and helps to distribute metallics and pearls evenly.

### PRODUCT AND ADDITIVES

- Concept Basecoat Blend Control


### SUITABLE SUBSTRATES

- Concept HS 2K Primer
- Sound existing surfaces, except for weak surfaces such as nitrocellulose or enamels.

### MIXING RATIO




- Ready For Use.

### SPRAY GUN AND PRESSURE

SPRAY GUN & PRESSURE:	<ul style="list-style-type: none"><li>• Use 1.2 – 1.4mm through a suction feed gun.</li><li>• Pressure at 350 – 450 kPa (Gravity feed is slightly higher pressure).</li></ul>	
-----------------------	---	---

## APPLICATION

- All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.
- Apply one to two even coats.

SPRAYING VISCOSITY:	<ul style="list-style-type: none"> <li>• 13 – 15 seconds B4 cup at 25°C.</li> </ul>	 13-15 SECONDS
FLASH-OFF TIME:	<ul style="list-style-type: none"> <li>• If required, 5 – 10 minutes between coats at 25°C.</li> </ul>	
DRYING:	<ul style="list-style-type: none"> <li>• 15 – 20 minutes at 25°C for a Dry Film Thickness of 7 – 10 Micron.</li> </ul>	

## TECHNICAL INFORMATION

<b>COLOUR:</b>	Clear
<b>COVERAGE:</b>	8 m <sup>2</sup> /L @ 10 Micron Dry Film Thickness.
<b>VOC:</b>	763 g/L
<b>PACKAGING:</b>	1LT, 4LT
<b>ITEM CODE:</b>	A04C/BBLEND
<b>SHELF LIFE:</b>	12 Months

The above information is reliable and accurate to the best of our knowledge at the time of preparation. Any recommendations or suggestions made are without warranty or guarantee. Users assume all responsibility since the conditions of use are beyond our control.

**REVISED: 08 April 2013**

**REPLACES ISSUE: 3 May 2010**