



# TECHNICAL DATA SHEET

## BEVAN BLACK (CHASSIS)

### PRODUCT DESCRIPTION

This is a high coverage and fast drying industrial enamel for application over primed steel. It has been specifically designed for use on truck chassis and underbodies.

### PRODUCT AND ADDITIVES

- Concept Bevan Black (Chassis)
- Concept Enamel Thinner




### SUITABLE SUBSTRATES

- Concept Enamel Primer
- Concept Zinc Phosphate Primer
- Concept 1K Etch Primer
- Concept Universal 4000 Primer
- Sound Enamel surfaces.

### MIXING RATIO




- Up to 20% reduction with Concept Enamel Thinner may be required.

### SPRAY GUN AND PRESSURE

SPRAY GUN & PRESSURE:	<ul style="list-style-type: none"><li>• Use 1.3 –1.5 mm gravity feed or suction feed gun.</li><li>• Pressure at 340 – 360 kPa.</li></ul>	
-----------------------	--	---

## APPLICATION

- All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.
- Apply one light coat and one even full coat. Avoid heavy wet coats.

SPRAYING VISCOSITY:	<ul style="list-style-type: none"> <li>• 18 – 19 seconds B4 cup at 25°C.</li> </ul>	 18-19 Seconds
FLASH-OFF TIME:	<ul style="list-style-type: none"> <li>• 5 minutes between coats at 25°C.</li> </ul>	
DRYING:	<ul style="list-style-type: none"> <li>• 2 – 3 hours at 25°C for a Dry Film Thickness of 40 – 50 Micron.</li> </ul>	

## TECHNICAL INFORMATION

<b>COLOUR:</b>	Black
<b>COVERAGE:</b>	6 m <sup>2</sup> /L @ 50 Micron Dry Film Thickness.
<b>VOC:</b>	451 g/L
<b>PACKAGING:</b>	1LT, 4LT, 20LT
<b>ITEM CODE:</b>	A06C/BEVB
<b>SHELF LIFE:</b>	12 Months

The above information is reliable and accurate to the best of our knowledge at the time of preparation. Any recommendations or suggestions made are without warranty or guarantee. Users assume all responsibility since the conditions of use are beyond our control.

**REVISED: 18 April 2013**

**REPLACES ISSUE: 1 December 2004**

***Bevan Black (Chassis)***

***Page 2 of 2***