



TECHNICAL DATA SHEET

CONCEPT GLASS PROMOTER

(FOR GLASS SPLASHBACKS)

PRODUCT DESCRIPTION

This newly developed Concept Glass Promoter is an adhesion promoter, specifically designed to adhere to a glass substrate. It is a ready for use product with good flow properties. It can be topcoated with either Concept's No Mix Basecoat or Concept's Unicolour 600 2K Colours.

PRODUCT AND ADDITIVES

- Concept Antistatic Cleaner
- Concept Glass Promoter




SUITABLE SUBSTRATES

- Glass.

MIXING RATIO



- Ready for use. Although up to 5% thinning with Concept's 2K Thinner can be used, if required.

SPRAY GUN AND PRESSURE

SPRAY GUN & PRESSURE:	<ul style="list-style-type: none">• 1.2 - 1.5 mm through a suction feed.• Pressure is 350 – 450 kPa (gravity feed will apply)	
-----------------------	--	---

APPLICATION

- Clean the glass surface thoroughly either with Concept's Antistatic Cleaner or a detergent, ensuring all contaminants are removed.
- If a detergent is used, ensure that no residues are left behind, by thoroughly rinsing the glass surface with water and allowing it to dry fully.
- Using a suitable lint free cloth, apply an even film (without streaks) of the Concept Glass Promoter to the surface of the glass.
- Or alternately, using the recommended spraying equipment, apply one to two even coats.
- Allow the Concept Glass Promoter to dry for 30 minutes before applying the Basecoat or 2K colour.
- Apply the Basecoat or 2K colour in accordance with the appropriate Technical Data Sheet.
- In the case where strong glues are used, 5% by volume of Concept Universal Hardener (MS) can be added to the Basecoat colour, to activate it. Or alternately apply Concept's MS-22 2K Clear over the Basecoat colour to protect it from the glue.

SPRAYING VISCOSITY:	<ul style="list-style-type: none"> • 12 – 13 seconds B4 cup at 25°C. 	 <p>12-13 SECONDS</p>
DRYING:	<ul style="list-style-type: none"> • 30 minutes at 25°C for a Dry Film Thickness of 7 – 10 Micron. 	

TECHNICAL INFORMATION

COLOUR:	Milky Clear Solution
COVERAGE:	10 m ² /L @ 10 Micron Dry Film Thickness.
VOC:	780 g/L
PACKAGING:	4LT, 20LT
ITEM CODE:	A03C/GLASSPRO
SHELF LIFE:	12 Months

The above information is reliable and accurate to the best of our knowledge at the time of preparation. Any recommendations or suggestions made are without warranty or guarantee. Users assume all responsibility since the conditions of use are beyond our control.

REVISED: 08 April 2013

REPLACES ISSUE: 19 August 2010