



TECHNICAL DATA SHEET

RUBBERISED UNDERCOAT

(SPRAYPAK)

PRODUCT DESCRIPTION

Concept Paint's Rubberised Undercoat is a flexible paintable coating for use in wheel wheels, quarter panels, fenders and all automotive under carriages. It has excellent moisture, chemical and corrosion resistance, whilst creating an effective sound barrier that reduces vibration and noise.

PRODUCT AND ADDITIVES

- Concept Rubberised Undercoat Spraypak

SUITABLE SUBSTRATES

- Sound existing finishes.
- Metal surfaces primed with Concept 1K Etch Primer Spraypak.

SUBSTRATE PREPARATION

- All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.
- Mask off surrounding areas to avoid overspray.

MIXING

- Ready for Use
- Invert and shake the can thoroughly, until the agitation ball can be heard (two to three minutes). Continue to shake the can during application.

APPLICATION

- Spray in an even overlapping pattern from a distance of approximately 25 centimetres.
- Apply two to three even coats to gradually increase film thickness.
- Avoid heavy coats which may run.
- Allow 5 minutes flash off between coats.

Drying @ 25°C and 40 micron DFT:	6 hours
---	---------

- Note: Can be recoated, once dry, with any Concept Paints topcoat. It will not bleed through when top coated.

AFTER USE

- Turn the can upside down and spray until the jet clears.
- Any over spray maybe cleaned up with Mineral Turps.

TECHNICAL INFORMATION

COLOUR:	Black
COVERAGE:	5 m ² /511g @ 40 Micron Dry Film Thickness.
PACKAGING:	511g
ITEM CODE:	A02C/RU/511G
SHELF LIFE:	12 Months

The above information is reliable and accurate to the best of our knowledge at the time of preparation. Any recommendations or suggestions made are without warranty or guarantee. Users assume all responsibility since the conditions of use are beyond our control.

REVISED: 28 April 2015

REPLACES ISSUE: 10 March 2014