



## TECHNICAL DATA SHEET

### **UNI-HARDENER (MS)** SLOW, NORMAL, FAST, SUPERFAST

#### PRODUCT DESCRIPTION

A range of universal 2 Pack Hardeners (MS) specifically designed for use with Polyurethane Paints.

#### PRODUCT AND ADDITIVES

- Concept Uni-Hardener (MS) Super Fast
- Concept Uni-Hardener (MS) Fast
- Concept Uni-Hardener (MS) Normal
- Concept Uni-Hardener (MS) Slow



#### MIXING RATIO

- 2 parts of any 2 Pack Product by volume.
- 1 part Concept Uni-Hardener (MS) by volume.

#### APPLICATION

- ***Refer to the relevant Technical Data Sheet on the product used for application instructions.***

## HARDENER USAGE

### Hardener usage for Low Temperature Baking

	Hardener	25°C	30°C	35°C	40°C	45°C	50°C	55°C	60°C
Only Panel Work	Super Fast			35 minutes					
	Fast							35 minutes	
Full Respray	Fast								35 minutes
	Normal								35 minutes
	Slow								35 minutes

### Hardener usage for Ambient Cure (Room Temperature)

	Hardener	10°C	15°C	20°C	25°C	30°C	35°C	40°C
Only Panel Work	Super Fast							
	Fast							
Full Respray	Fast							
	Normal							
	Slow							

***Note: Products are only recommended for use as shown in the shaded areas. Information is based on Concept Products. When using with other Company's product, adjustments may be required.***

## TECHNICAL INFORMATION

<b>COLOUR:</b>	Crystal Clear Solution
<b>VOC:</b>	Slow: 594 g/L, Normal: 593 g/L, Fast: 578 g/L, Super Fast: 573 g/L
<b>PACKAGING:</b>	500ML, 1LT
<b>ITEM CODE:</b>	A04C/UNIMS
<b>SHELF LIFE:</b>	6 Months - Should be sealed tightly at all times as product reacts with moisture and humidity.

The above information is reliable and accurate to the best of our knowledge at the time of preparation. Any recommendations or suggestions made are without warranty or guarantee. Users assume all responsibility since the conditions of use are beyond our control.

**REVISED: 07 May 2013**

**REPLACES ISSUE: 1 December 2004**