


Product Name	
Full Product Name	034 Concrete Paint Converter
Type of Product	1K acrylic additive
Description	Concept 034 Concrete Paint Converter is a solvent based additive used with Concept Unicryl 3000 System colours to convert the colour into an acrylic based concrete coating for most concrete surfaces. It aids in drying of the coating which improves hardness, adhesion and wear resistance in high traffic areas.

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
034 Concrete Paint Converter	0.0	0.0	0.839	7.00	839.3	7.00
Unicryl 3000 Series colours	Depending on the colour					









Properties
<ul style="list-style-type: none"> Converts Unicryl 3000 System colours into an acrylic based concrete coating Improves hardness, adhesion and wear resistance

Substrates
<ul style="list-style-type: none"> Most properly prepared and unpainted concrete surfaces Existing surfaces in sound condition



Substrate Preparation

 <p>All Substrates</p>	<ul style="list-style-type: none"> All surfaces must be clean, dry and free from oil and grease. Steel trowelled concrete surfaces must be acid washed prior to application. Pre-painted surfaces in sound condition must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application. Poor surfaces should be removed, using either sandblasting or high pressure water.
--	--

Product Preparation

		Concept Unicryl 3000 colour	Concept 034 Concrete Paint Converter
 <p>Reducer</p>	Not required - product supplied ready for use		
 <p>Pot life @ 25°C (77°F)</p>	N/A		
  <p>Application</p>	Number of coats	2 Apply two to three even coats. Avoid heavy wet coats.	
	DFT Recommended	40-50 µm 1.6-2.0 mil	
 <p>Flash off time @ 25°C (77°F)</p>	5-10 min between coats		
 <p>Drying</p>	Air Dry @ 25°C (77°F)	40-60 min	

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Remarks	
	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning
Use recommended Concept Paints 035 Gunwash

Dry Film Properties	After 7 days drying, <u>when compared to similar technology products.</u>
Adhesion	Very good
Wear resistance	Very good
Hardness	Very good

Product Data	
Colour	Water white
Theoretical Coverage	Approx. 5.0 m ² /L (205 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature, away from sunlight.

Product Packaging		
Product Code	Product Name	Package Size
IN03490000004	034 Concrete Paint Converter	4L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
office@conceptpaints.com.au
www.conceptpaints.com.au