

Date: 11th December 2020
Version:02

Technical Data Sheet

Product Name	
Full Product Name	118 Cold Gal
Type of Product	1K Cold Galvanising Primer
Description	Concept 118 Cold Gal is a Zinc Rich Primer designed to give corrosion protection in a galvanised form. For use on all ferrous metals which provides a protection barrier from rusting. Ideal for all highly corrosive areas. Steel structures, bridges, tanks and wharves.

Products					
Product Name	Volume Solids %	Weight Solids %	Density g/mL lbs/US gal		VOC g/L lbs/US gal
118 Cold Gal	70.9	75.6	1.258	8.99	530.9 4.43
804 Enamel Thinner	0.0	0.0	0.802	6.69	802.0 6.69

Properties
<ul style="list-style-type: none">fast drying
<ul style="list-style-type: none">Easy application
<ul style="list-style-type: none">High build and good opacity

Substrates
<ul style="list-style-type: none">Steel or Galvanised Surfaces

Date: 11th December 2020
Version:02

Technical Data Sheet











Substrate Preparation



All Substrates

All surfaces must be thoroughly sanded and cleaned from any rust or contamination then clean with Concept Wax & Grease Remover, Prior to application.



Product Preparation

	Reducer	Up to 10% reduction with concept 804 Enamel Thinner, if required			
	Pot life @ 25°C (77°F)	N/A			
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	18-19 s 16-17 s		
  	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
		Gravity feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		Suction feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		HVLP	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats	2	Apply one coat followed by one even full coat. Avoid heavy wet coats.		
	DFT Recommended	30-40 µm 1.2-1.6 mils			
	Flash off time @ 25°C (77°F)	5 min between coats			
	Drying	Air Dry @ 25°C (77°F)	30-40 min and 16 Hours before recoating		
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.					

Date: 11th December 2020
Version:02

Technical Data Sheet

Remarks

	Stir all products thoroughly each time before use.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints 035 Gunwash
--

Dry Film Properties

when compared to similar technology products.

Gloss	Matt
Adhesion	Excellent
Metal Protection	Excellent

Product Data

Colour	Silver/Grey
Theoretical Coverage	Approx. 8.0 m ² /L (245 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature, away from sunlight.

Product Packaging

Product Code	Product Name	Package Size
IN11880000001 IN80492000001	118 Cold Gal 804 Enamel Thinner	1L, 4L 1L, 4L, 20L

Date: 11th December 2020
Version:02

Technical Data Sheet

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
office@conceptpaints.com.au
www.conceptpaints.com.au