Date: 24<sup>th</sup> February 2022 Version:03

## **Technical Data Sheet**

Product Name	
Full Product Name	2K Matt Clear
Type of Product	2K Matt Acrylic Urethane Clearcoat
Description	Concept 2K Matt Clear is a high performance 2K clear coat, designed specifically to achieve a matt finish (10-15% gloss level), replicating the latest OEM matt offering. It is characterized by excellent flow, high chemical resistance and hardness properties.

Products						
Product Name	Volume Solids %	Weight Solids %	Den g/mL lb	<b>sity</b> bs/US gal	VC g/L lb	<b>C</b> s/US gal
2K Matt Clear	38.8	48.8	1.069	8.92	547.5	4.57
MS Uni Harderner Slow	35.4	40.9	1.004	8.38	593.8	4.96
MS Uni Hardener Normal	33.3	39.9	0.986	8.23	593.1	4.95
MS Uni Hardener Fast	33.6	40.2	0.968	8.08	578.3	4.83
MS Uni Hardener Super Fast	31.5	38.9	0.938	7.83	572.7	4.78
2K Thinner Slow	0.0	0.0	0.893	7.45	892.7	7.45
2K Thinner	0.0	0.0	0.882	7.36	881.9	7.36
2K Thinner Fast	0.0	0.0	0.872	7.27	871.5	7.27

#### **Properties**

- High performance
- Fast drying
- Excellent through cure
- Excellent levelling and flow
- Even matt gloss effect





Version:03

### Substrates

- Concept No Mix system colours
- Concept Unicolour 900 2K Basecoat system colours
- Sound existing surfaces, except for unstable surfaces such as nitrocellulose or enamels

**Technical Data Sheet** 

Substrate Preparation	
All Substrates	All surfaces must be cleaned with Concept Wax & Grease Remover and free from any contamination prior to application.

Pro	oduct Prepar	ation				
	Mixing Ratio 2:1 (by volume)			Concept 2K Matt Clear	Concept MS Uni Hardener	Concept MS-22 Hardener
		Large are	eas	2 parts	-	1 part
		Small are	eas	2 parts	1 part	-
	Reducer	Up to 10% (v/v) of Concept 2K Thinner, if required.				
AB	Pot life @ 25°C (77°F)	2-3 hours				
S	Spray viscosity @ 25°C (77°F)	BSB 4 Cup 18-19 s   Ford 4 Cup 16-17 s				



# **Technical Data Sheet**

Version:03

	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
	. 1	Gravity feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
<b>≜`\</b> ⊣∨lp		Suction feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		HVLP	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats	2 Apply two even full coats. Avoid heavy wet coats.			
	DFT Recommended	40-50 μm 1.6-2.0 mils			
<u>/</u> ↑/ <u>↑</u> /	Flash off time @ 25°C (77°F)	5-10 min between coats			
	Drying	Air Dry 16-24 hours			
Low Bake @ 50°C (122°F) 30-40 min					

Remarks	
	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
PF/°C	Surface temperature must always be a minimum of 3°C (5°F) above dew point.
NOTE:	Always ensure adequate and thorough flash off of the basecoat before application of this clear coat (otherwise damage to the appearance may occur).



Date: 24<sup>th</sup> February 2022 Version:03

## **Technical Data Sheet**

## **Equipment Cleaning**

Use recommended Concept Paints 035 Gunwash

Dry Film Properties	After 7 days drying, when compared to similar technology products.
Gloss@ 60°	10-15%
Hardness	Excellent
Chemical resistance	Excellent
Durability	Excellent

Product Data	
Colour	Hazy
Theoretical Coverage	Approx. 8.0 m <sup>2</sup> /L (325 ft <sup>2</sup> /US gal) @ recommended DF
Shelf Life	36 months in an unopened container at room temperature, away from sunlight.

Product Packaging		
Product Code	Product Name	Package Size
AU7239001000X	2K Matt Clear	1L, 4L
AU2139100000X	Universal (MS) Slow Hardener	500 mL, 1L
AU2139200000X	Universal (MS) Normal Hardener	500 mL, 1L
AU2139300000X	Universal (MS) Fast Hardener	500 mL, 1L
AU2139400000X	Universal (MS) Super Fast Hardener	500 mL, 1L
AU8319100000X	2K Thinner Slow	1L, 4L, 20L
AU8319200000X	2K Thinner	1L, 4L, 20L
AU8319300000X	2K Thinner Fast	1L, 4L, 20L



## **Technical Data Sheet**

Version:03

#### Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints 26-30 Charles Street St Marys NSW 2760 Sydney, Australia ph. +61 (2) 9673 2555 fax. +61 (2) 9623 1918 office@conceptpaints.com.au www.conceptpaints.com.au



Version:03

# **Technical Data Sheet**