

Technical Data Sheet

Product Name	
Full Product Name	2K Satin Black
Type of Product	2K acrylic urethane topcoat
Description	Concept 2K Satin Black is a high performance 2K black topcoat, formulated to achieve satin black finish in between high gloss and matt coatings. It is characterized by its excellent flow, coverage, chemical resistance and durability.

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
2K Satin Black	39.9	47.86	1.010	8.43	527.5	4.40
Universal (MS) Hardener Slow	35.4	40.9	1.004	8.38	593.8	4.96
Universal (MS) Hardener Normal	33.3	39.9	0.986	8.23	593.1	4.95
Universal (MS) Hardener Fast	33.6	40.2	0.968	8.08	578.3	4.83
Universal (MS) Hardener Super Fast	31.5	38.9	0.938	7.83	572.7	4.78
2K Thinner Slow	0.0	0.0	0.893	7.45	892.7	7.45
2K Thinner	0.0	0.0	0.882	7.36	881.9	7.36
2K Thinner Fast	0.0	0.0	0.872	7.27	871.5	7.27

Properties
<ul style="list-style-type: none"> • High performance and opacity
<ul style="list-style-type: none"> • Fast drying
<ul style="list-style-type: none"> • Excellent through cure
<ul style="list-style-type: none"> • Excellent levelling and flow
<ul style="list-style-type: none"> • Satin finish

Substrates

- Concept HS 2K Primer
- Sound existing surfaces, except for unstable surfaces such as nitrocellulose or enamels.

Substrate Preparation



All Substrates




All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.

Product Preparation



	Mixing Ratio 2:1 (by volume)	Concept 2K Matt Black		Concept Universal (MS) Hardener	
		2 parts		1 part	
	Reducer	Up to 10% (v/v) of Concept 2K Thinner, if required.			
	Pot life @ 25°C (77°F)	2-3 hours			
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	16-17 s 14-15 s		
	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
		Gravity feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		Suction feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
	HVLP	HVLP	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats	2-3	Apply one coat followed by one or two even full coats. Avoid heavy wet coats.		

Technical Data Sheet

Product Preparation cont

	DFT Recommended	40-50 µm 1.6-2.0 mils	
	Flash off time @ 25°C (77°F)	5-10 min between coats	
	Drying	Air Dry @ 25°C (77°F)	16-24 hours
		Low Bake @ 50°C (122°F)	30-40 min
<p>This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.</p>			

Remarks

	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints cleaner

Dry Film Properties

After 7 days drying, **when compared to similar technology products.**

Gloss 60°	45-55 GU (Gloss Units)
Chemical resistance	Excellent
Durability	Excellent

Product Data	
Colour	Black (Satin Gloss)
Theoretical Coverage	Approx. 9.0 m ² /L (365 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature, away from sunlight.

Product Packaging			
Product Code 1	Product Code 2	Product Name	Package Size
A06C/2KBLKSAT	3607002	2K Satin Black	1L, 4L
A04C/UNIMSS	2139100	Universal (MS) Hardener Slow	500 mL, 1L
A04C/UNIMSN	2139200	Universal (MS) Hardener Normal	500 mL, 1L
A04C/UNIMSF	2139300	Universal (MS) Hardener Fast	500 mL, 1L
A04C/UNIMSSF	2139400	Universal (MS) Hardener Super Fast	500 mL, 1L
A08C/2KTHS	8319100	2K Thinner Slow	1L, 4L, 20L
A08C/2KTHIN	8319200	2K Thinner	1L, 4L, 20L
A08C/2KTHF	8319300	2K Thinner Fast	1L, 4L, 20L

Safety
<p>For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.</p> <p>Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.</p>

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
info@conceptpaints.com.au
www.conceptpaints.com.au