


Product Name	
Full Product Name	2K Timber Clear (2:1)
Type of Product	2K polyurethane clearcoat
Description	Concept 2K Timber Clear (2:1) is a high gloss 2K clearcoat for timber substrates. It is characterised by its superior flow, very high gloss and exceptional chemical resistance, flexibility and hardness.

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
2K Timber Clear (2:1)	37.9	43.3	1.001	8.36	568.3	4.74
2K Timber Hardener	41.9	48.4	1.005	8.39	517.7	4.32
2K Thinner Slow	0.0	0.0	0.893	7.45	892.7	7.45
2K Thinner	0.0	0.0	0.882	7.36	881.9	7.36
2K Thinner Fast	0.0	0.0	0.872	7.27	871.5	7.27













Properties
<ul style="list-style-type: none"> • Superior flow • Excellent flexibility

Substrates
<ul style="list-style-type: none"> • Concept 1K Timber Sealer • Concept 2K Timber Sealer (4:1)



Substrate Preparation	
 All Substrates	All surfaces must be thoroughly sanded prior to application. Ensure all surfaces are clean and free from loose particles.

Technical Data Sheet

Product Preparation

	Mixing Ratio 2:1 (by volume)	Concept 2K Timber Clear (2:1)		Concept 2K Timber Hardener	
		2 parts		1 part	
	Reducer	5% (v/v) of Concept 2K Thinner may be added, if required			
	Pot life @ 25°C (77°F)	6-8 hours			
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	18-19 s 16-17 s		
   	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
		Gravity feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		Suction feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		HVLP	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats	2-3	Apply one coat followed by one or two even full coats. Avoid heavy wet coats.		
	DFT Recommended	50-60 µm 2.0-2.4 mils			
	Flash off time @ 25°C (77°F)	5-10 min between coats			
	Drying	Air Dry @ 25°C (77°F)	12-16 hours		
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.					

Technical Data Sheet

Remarks	
	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning	
Use recommended Concept Paints cleaner	

Dry Film Properties	
After 7 days drying, <u>when compared to similar technology products.</u>	
Hardness	Excellent
Chemical resistance	Excellent

Product Data	
Colour	Water white
Gloss	High
Theoretical Coverage	Approx. 7.0 m ² /L (285 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature away from sunlight.

Product Packaging			
Product Code 1	Product Code 2	Product Name	Package Size
A15/2KCLEAR	7769000	2K Timber Clear (2:1)	4L, 20L
A15/2KHARD	7939200	2K Timber Hardener	1L
A08C/2KTHS	8319100	2K Thinner Slow	4L, 20L, 60L
A08C/2KTHIN	8319200	2K Thinner	4L, 20L, 60L
A08C/2KTHF	8319300	2K Thinner Fast	4L, 20L, 60L

Safety

For professional use only. Read and follow all label and Safety Data Sheet (SDS) precautions before opening or using. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment (PPE). Ensure adequate ventilation.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
info@conceptpaints.com.au
www.conceptpaints.com.au