

Technical Data Sheet

Version: 02

Product Name	
Full Product Name	402 QD Factory Mixed Colours
Type of Product	1K Alkyd Enamel Topcoat
Description	Concept 402 QD Factory Mixed Colours are fast drying alkyd enamels with good gloss for quick and easy low build protection and beautification of primed steel. Particularly suited for tools, implements and equipment.

Products						
Product Name	Volume Solids %	Weight Solids %		nsity Ibs/US gal		DC bs/US gal
402 QD Golden Yellow Y14	46.5	54.1	0.984	8.22	452.4	3.78
402 QD Golden Yellow	46.6	54.2	0.985	8.23	452.6	3.80
402 QD New Cat Yellow	51.9	61.3	1.080	9.01	417.8	3.49
402 QD Post Office Red	46.4	52.7	0.964	8.05	456.5	3.81
402 QD Signal Red R13	46.4	52.7	0.964	8.05	456.5	3.81
402 QD Sapphire Blue	46.4	52.7	0.983	8.20	464.9	3.88
402 QD Orange X15	46.4	54.3	0.989	8.25	451.4	3.77
402 QD Mid Grey N52	47.8	57.6	1.048	8.75	444.9	3.71
804 Enamel Thinner	0.00	0.00	0.802	6.69	0.802	6.69

Properties

- Superior performance when compared to other QD enamels
- Fast drying
- High gloss
- Quick and easy application



Technical Data Sheet

Version: 02

Substrates

- Concept 109 Enamel Primer
- Concept 113 ZP Primer or 116 ZP Primer(HB)
- Concept 103 Etch Primer or 110 Metal Etch
- Concept 111 Universal Primer(HB)
- Previously painted enamel substrates in sound condition (always check before painting)

Substrate Preparation	
	All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application

Product Preparation					
	Reducer	Up to 20% (v/v) Concept 804 Enamel Thinner, if required			
AB	Pot life @ 25°C (77°F)	N/A			
S	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup			
	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
>1		Gravity Feed	1.3-1.5 mm 0.051-0.059"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		Suction feed	1.3-1.5 mm 0.051-0.059"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
HVLP		HVLP	1.3-1.5 mm 0.051-0.059"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
		Airless, Air Assisted, Electrostatic	•		uctions.



Technical Data Sheet

Version: 02

Product Preparation cont.				
	Number of coats	2 Apply one light coat followed by one even full coat. Avoid heavy wet coats.		
	DFT Recommended	40-50 μm 2.0 mils		
$\frac{\left\langle \uparrow \right\rangle \uparrow \left\langle \uparrow \right\rangle}{\left\langle \circ \right\rangle \circ \left\langle \circ \circ \circ \circ \circ \circ \circ \circ \left\langle \circ \circ \circ \circ \circ \circ \circ \circ$	Flash off time @ 25°C (77°F)	5 min between coats		
	Drying	Air Dry @ 25°C (77°F)	4-5 hours	
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.				

Remarks	
	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
₽°F / °C	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints 035 Gunwash

Dry Film Properties	After 7 days drying, when compared to similar technology products.	
Gloss	High	
Water resistance	Good	
Petrol resistance	Good	
Durability	Good	



Technical Data Sheet

Version: 02

Product Data	
Theoretical Coverage	Approx. 6.0 m ² /L (245 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature away from sunlight.

Product Packaging		
Product Code	Product Name	Package Size
IN4021003000X	402 QD Golden Yellow Y14	1L, 4L, 20L
IN4021020000X	402 QD Golden Yellow	1L, 4L, 20L
IN4021021000X	402 QD New Cat Yellow	1L, 4L, 20L
IN4023027000X	402 QD Post Office Red	1L, 4L, 20L
IN4023005000X	402 QD Signal Red R13	1L, 4L, 20L
IN4024023000X	402 QD Sapphire Blue	1L, 4L, 20L
IN4022021000X	402 QD Orange X15	1L, 4L, 20L
IN4026027000X	402 QD Mid Grey N52	1L, 4L, 20L
IN8049200000X	804 Enamel Thinner	1L, 4L, 20L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

402 QD Factory Mixed Colours 1K Alkyd Enamel Topcoat



Date: 21st July 2021

Technical Data Sheet

Version: 02

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints 26-30 Charles Street St Marys NSW 2760 Sydney, Australia ph. +61 (2) 9673 2555 fax. +61 (2) 9623 1918 office@conceptpaints.com.au www.conceptpaints.com.au