

Technical Data Sheet

Product Name	
Full Product Name	451 Silver Gal (2 in 1)
Type of Product	1K Fast Drying Zinc Topcoat
Description	Concept 451 Silver Gal (2 in 1) is a very fast drying 1K industrial paint producing the appearance of galvanised steel. It is a 2 in 1 an anticorrosive primer and topcoat in one.

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
451 Silver Gal (2 in 1)	37.9	44.6	0.958	7.99	530.9	4.43
804 Enamel Thinner	0.0	0.0	0.802	6.69	802.0	6.69

Properties
<ul style="list-style-type: none"> fast drying
<ul style="list-style-type: none"> Easy application
<ul style="list-style-type: none"> Low build and good opacity

Substrates
<ul style="list-style-type: none"> 109 Enamel Primer - Grey
<ul style="list-style-type: none"> 113 ZP Primer
<ul style="list-style-type: none"> 103 Etch Primer
<ul style="list-style-type: none"> 111 Universal Primer(HB)
<ul style="list-style-type: none"> Steel or Galvanised Surfaces

Technical Data Sheet









Substrate Preparation



All Substrates

All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.



Product Preparation

	Reducer	Up to 10% reduction with concept 804 Enamel Thinner, if required			
	Pot life @ 25°C (77°F)	N/A			
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup	18-19 s		
		Ford 4 Cup	16-17 s		
	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
		Gravity feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		Suction feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		HVLP	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats	2	Apply one coat followed by one even full coat. Avoid heavy wet coats.		
	DFT Recommended	30-40 µm 1.2-1.6 mils			
	Flash off time @ 25°C (77°F)	5 min between coats			
	Drying	Air Dry @ 25°C (77°F)	40-60 min		

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Technical Data Sheet

Remarks

	Stir all products thoroughly each time before use.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints 035 Gunwash
--

Dry Film Properties

when compared to similar technology products.

Gloss	Satin
Adhesion	Excellent
Metal Protection	Excellent

Product Data

Colour	Silver
Theoretical Coverage	Approx. 6.0 m ² /L (245 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature, away from sunlight.

Product Packaging

Product Code	Product Name	Package Size
IN4518000001	451 Silver Gal (2 in 1)	1L, 4L, 20L
IN80492000001	804 Enamel Thinner	1L, 4L, 20L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
office@conceptpaints.com.au
www.conceptpaints.com.au