

Date: 21st October 2016

Technical Data Sheet

Version:01

Product Name

Full Product Name	Bevan Black (Chassis)
Type of Product	1K enamel topcoat
Description	Concept Bevan Black (Chassis) is an industrial enamel topcoat, designed for use on truck chassis and underbodies. It is characterized by its high coverage and fast drying.

Products

Product Name	Volume Solids	Weight Solids	Density		VOC	
	%	%	g/mL	lbs/US gal	g/L	lbs/US gal
Bevan Black (Chassis)	48.2	54.0	0.965	8.05	443.7	3.70
Enamel Thinner	0.0	0.0	0.802	6.69	802.0	6.69

Properties

<ul style="list-style-type: none">• High coverage
<ul style="list-style-type: none">• Good flow
<ul style="list-style-type: none">• Fast drying

Substrates

<ul style="list-style-type: none">• Concept Enamel Primer
<ul style="list-style-type: none">• Concept Zinc Phosphate Primer
<ul style="list-style-type: none">• Concept 1K Etch Primer
<ul style="list-style-type: none">• Concept Universal 4000 Primer
<ul style="list-style-type: none">• Sound enamel surfaces

Technical Data Sheet

Substrate Preparation



All Substrates

All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.

Product Preparation



Reducer

Up to 20% reduction with Concept Enamel Thinner, if required



Pot life @ 25°C (77°F)

N/A



Spray viscosity @ 25°C (77°F)

BSB 4 Cup
Ford 4 Cup

18-19 s
16-17 s



Spray equipment

Gun type

Fluid tip

Spray pressure

Spray Distance

Gravity feed

1.3-1.4 mm
0.051-0.055"

200-240 kPa
2.0-2.4 bar
30-35 psi

15-20 cm
6-8 inch

Suction feed

1.3-1.4 mm
0.051-0.055"

200-240 kPa
2.0-2.4 bar
30-35 psi

15-20 cm
6-8 inch



HVLP

1.2-1.3 mm
0.047-0.051"

40-70 kPa
0.4-0.7 bar
6-10 psi

15-20 cm
6-8 inch



Number of coats

2-3

Apply one coat followed by one or two even full coats. Avoid heavy wet coats.



DFT Recommended

40-50 µm
1.6-2.0 mils



Flash off time @ 25°C (77°F)

5 min between coats



Drying

Air Dry
@ 25°C (77°F)

2-3 hours

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Technical Data Sheet

Remarks



Stir all products thoroughly each time before use.
Stir the mixture well after the weigh-out of the components.



Surface temperature must always be a minimum of 3°C
(5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints cleaner

Dry Film Properties

After 7 days drying,
when compared to similar technology products.

Gloss

High

Adhesion

Excellent

Metal Protection

Excellent

Product Data

Colour

Black

Theoretical Coverage

Approx. 6.0 m²/L (245 ft²/US gal) @ recommended DFT

Shelf Life

36 months in an unopened container
at room temperature, away from sunlight.

Product Packaging

Product Code 1	Product Code 2	Product Name	Package Size
A06C/BEVB A08C/ENA	3527004 8049200	Bevan Black (Chassis) Enamel Thinner	1L, 4L, 20L 1L, 4L, 20L, 60L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
info@conceptpaints.com.au
www.conceptpaints.com.au