


# Technical Data Sheet

Product Name	
Full Product Name	<b>CP01 White and CP06 Black</b>
Type of Product	Concentrated tinters
Description	Concept CP01 White and CP06 Black are concentrated tinters, which can be mixed with a range of different universal binders. They offer the flexibility to choose a binder for a specific end application.









Products						
Product Name	Volume Solids	Weight Solids	Density		VOC	
	%	%	g/mL	lbs/US gal	g/L	lbs/US gal
CP01 White	70.0	84.7	1.908	15.93	291.3	2.43
CP06 Black	55.5	56.5	1.097	9.16	477.1	3.98

Properties
<ul style="list-style-type: none"> <li>• Can be mixed with a range of different universal binders.</li> <li>• For further information, please refer to relevant Technical Data Sheet for base product.</li> </ul>

Substrates
<ul style="list-style-type: none"> <li>• Refer to relevant Technical Data Sheet for base product.</li> </ul>



Substrate Preparation	
 <b>All Substrates</b>	<p>All surfaces must be thoroughly sanded and cleaned with Concept Wax &amp; Grease Remover prior to application. For further information, please refer to relevant Technical Data Sheet for base product.</p>

## Product Preparation

	<b>Reducer</b>	Refer to relevant Technical Data Sheet for base product.	
	<b>Pot life</b> @ 25°C (77°F)	N/A	
	<b>Spray viscosity</b> @ 25°C (77°F)	<b>BSB 4 Cup</b> <b>Ford 4 Cup</b>	Refer to relevant Technical Data Sheet for base product.
	<b>Spray equipment</b>	Refer to relevant Technical Data Sheet for base product.	
	<b>Number of coats</b>	Refer to relevant Technical Data Sheet for base product.	
	<b>DFT Recommended</b>	Refer to relevant Technical Data Sheet for base product.	
	<b>Flash off time</b> @ 25°C (77°F)	Refer to relevant Technical Data Sheet for base product.	
	<b>Drying</b>	Refer to relevant Technical Data Sheet for base product.	

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

## Remarks

	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

## Equipment Cleaning

Use recommended Concept Paints 035 Gunwash

# Technical Data Sheet

## Dry Film Properties

After 7 days drying,  
when compared to similar technology products.

Refer to relevant Technical Data Sheet for base product.

## Product Data

<b>Colour</b>	White, Black
<b>Theoretical Coverage</b>	Refer to relevant Technical Data Sheet for base product
<b>Shelf Life</b>	36 months in an unopened container at room temperature, away from sunlight.

## Product Packaging

Product Code	Product Name	Package Size
AU47060000004	CP01 White	4L
AU47070000004	CP06 Black	4L

## Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints  
26-30 Charles Street  
St Marys NSW 2760  
Sydney, Australia

ph. +61 (2) 9673 2555  
fax. +61 (2) 9623 1918  
office@conceptpaints.com.au  
www.conceptpaints.com.au