

Technical Data Sheet

Product Name	
Full Product Name	EP-41 Epoxy Primer
Type of Product	2K chromate free epoxy-polyamide primer
Description	Concepts' EP-41 Epoxy Primer is a 2K, chromate free epoxy-polyamide primer surfacer characterised by excellent adhesion to any metal substrate. Its unique formulation ensures a primer, which is very easy to sand and is suitable for use under any topcoat. It has very good anti-corrosive properties, with outstanding flexibility, chemical and water resistance.

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
EP-41 Epoxy Primer Grey	49.1	70.1	1.518	12.67	454.4	3.79
EP-41 Epoxy Primer White	49.7	71.0	1.551	12.94	449.0	3.75
EP-41 Epoxy Primer Black	49.3	66.8	1.377	11.49	456.9	3.81
EP-41 Primer Hardener	31.5	38.9	0.938	7.83	572.7	4.78
EP-41 Primer Hardener Fast	28.7	31.1	0.901	7.52	620.6	5.18
2K Thinner Slow	0.0	0.0	0.893	7.45	892.7	7.45
2K Thinner	0.0	0.0	0.882	7.36	881.9	7.36
2K Thinner Fast	0.0	0.0	0.872	7.27	871.5	7.27

Properties
<ul style="list-style-type: none"> • Excellent good anti-corrosive properties
<ul style="list-style-type: none"> • Outstanding flexibility
<ul style="list-style-type: none"> • Excellent adhesion and durability
<ul style="list-style-type: none"> • Easy to sand
<ul style="list-style-type: none"> • Excellent chemical and water resistance
<ul style="list-style-type: none"> • Suitable for use under all CONCEPT Paints Topcoats.

Substrates

- Mild Steel and Steel Alloy surfaces
- Stainless steel grade 316
- Aluminium, Zincalume, Zinccanear
- Galvanised steel
- Glass reinforced polyester (GRP & general types of fibreglass body parts)
- Sound, cured and properly prepared existing surfaces

Substrate Preparation



All Substrates

All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application. All metal surfaces must be sanded and cleaned with Concept Anti-static Cleaner. Lightly rusted surfaces must be treated with Concept 025 Rust Converter.

NOTE: Ensure complete and thorough removal of residual rust converter before applying this product.

Product Preparation

	Mixing Ratio 4:1 (by volume)			Concept EP-41 Primer	Concept EP-41 Primer Hardener
				4 parts	1 part
	Reducer	10-20% (v/v) of Concept 2K Thinner, if required.			
	Pot life @ 25°C (77°F)	6 hours			
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	17-19 s	15-17 s	

Technical Data Sheet

Product Preparation cont

Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
	Gravity feed	2.0 mm 0.079"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
	Suction feed	2.0 mm 0.079"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
	HVLP	1.5-1.8 mm 0.059-0.071"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Airless Air Assisted Electrostatic	Consult the manufacturer's instructions.		
	Number of coats	2-3 coats	Apply one coat followed by two even full coats. Avoid heavy wet coats.	
	DFT Recommended	40-50 µm 1.6-2.0 mils		
	Flash off time @ 25°C (77°F)	5 min between coats		
	Drying	Air Dry @ 25°C (77°F)	3-4 hours	
		Low Bake @ 50°C (122°F)	30-40 min	
	Sanding	Wet sand with P600-P800 or Dry sand with P500-P800 before applying finish coat		

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Remarks

	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.
NOTE:	Ensure the complete removal of any residue of Rust Converter before applying this primer.

Equipment Cleaning

Use recommended Concept Paints 035 Gunwash

Dry Film Properties

After 7 days drying,
when compared to similar technology products.

Hardness	Excellent
Flexibility	Excellent
Chemical and water resistance	Excellent
Corrosion protection	Excellent
Sanding	Excellent

Product Data

Colour	White, Grey, Black
Theoretical Coverage	Approx. 8 m ² /L (325 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature away from sunlight.

Product Packaging

Product Code	Product Name	Package Size
AU1416200000X	EP-41 Epoxy Primer Grey	1L, 4L,
AU14162000005N	EP-41 Epoxy Primer Grey	5LT (Kit)
AU1416000000X	EP-41 Epoxy Primer White	1L, 4L,
AU14160000005N	EP-41 Epoxy Primer White	5LT (Kit)
AU1417000000X	EP-41 Epoxy Primer Black	1L, 4L,
AU14170000005N	EP-41 Epoxy Primer Black	5LT (Kit)
AU1419200000X	EP-41 Primer Hardener	250mL, 1L
AU1419300000X	EP-41 Primer Hardener Fast	250mL, 1L
AU8319100000X	2K Thinner Slow	1L, 4L, 20L
AU8319200000X	2K Thinner	1L, 4L, 20L
AU8319300000X	2K Thinner Fast	1L, 4L, 20L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
office@conceptpaints.com.au

Technical Data Sheet