

Technical Data Sheet

Product Name	
Full Product Name	Eurolak 2K HS Clearcoat
Type of Product	2K low VOC acrylic urethane clearcoat
Description	<p>Concept Eurolak 2K HS Clear is a specifically designed to provide a high performance high solid clear over Concept's basecoat systems. It is characterised by superior flow, producing a very high gloss finish, with exceptional chemical resistance and hardness.</p> <p>The Eurolak 2K HS Clear has been developed from European technology and is suitable for all conditions and climates.</p>

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
Eurolak 2K HS Clearcoat	45.5	41.6	0.990	8.26	507.4	4.23
Eurolak Hardener	52.0	58.8	1.026	8.56	421.7	3.52

Properties
<ul style="list-style-type: none"> High performance, chemical resistance and durability
<ul style="list-style-type: none"> Excellent levelling and flow

Substrates
<ul style="list-style-type: none"> Concept No Mix Basecoat System colours
<ul style="list-style-type: none"> Concept Unicolour 900 2K Basecoat System colours
<ul style="list-style-type: none"> Sound existing surfaces, except for unstable surfaces such as nitrocellulose or enamels

Technical Data Sheet

Substrate Preparation



All Substrates


All surfaces must be clean and free from any contamination prior to application.

Product Preparation

	Mixing Ratio 3:1 (by volume)			Concept Eurolak 2K HS Clear	Concept Eurolak Hardener
				3 parts	1 part
	Reducer	Not required.			
	Pot life @ 25°C (77°F)	6-8 hours			
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	18-19 s 16-17 s		
 	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
		Gravity feed	1.2-1.5 mm 0.047-0.059"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		Suction feed	1.2-1.5 mm 0.047-0.059"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		HVLP	1.3-1.4 mm 0.051-0.055"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats	1.5-2	Apply one and a half or two coats. Avoid heavy wet coats.		
	DFT Recommended	50-60 µm 2.0-2.8 mils			
	Flash off time @ 25°C (77°F)	5-10 min between coats (if 2 coats)			



Technical Data Sheet

Product Preparation cont

 Drying	Air Dry @ 25°C (77°F)	12-16 hours
	Low Bake @ 50°C (122°F)	30-40 min

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Remarks

	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints cleaner.

Dry Film Properties

After 7 days drying,
when compared to similar technology products.

Gloss	Very high
Durability	Very high
Hardness	Excellent
Chemical resistance	Excellent

Product Data

Colour	Water white
Theoretical Coverage	Approx. 8 m ² /L (325 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature away from sunlight.

Technical Data Sheet

Product Packaging

Product Code 1	Product Code 2	Product Name	Package Size
AU74290000003		Euroлак 2K HS Clear	3L
AU74290000004N		Euroлак 2K HS Clear (3:1) Kit	4L (Kit)
AU74292000001		Euroлак Hardener	1L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
info@conceptpaints.com.au
www.conceptpaints.com.au