


# Technical Data Sheet

| Product Name      |  |
|-------------------|--|
| Full Product Name | <b>Infra-Red Primer Hardener</b>   |
| Type of Product   | Infra Red curing isocyanate hardener   |
| Description       | Infra-Red Primer Hardener is an isocyanate hardener, specifically designed to be used with Concept Paints' HS 2K Primer range for curing using both, short and medium wave, Infra-Red equipment. |

| Products                  |                 |                 |         |            |       |            |
|---------------------------|-----------------|-----------------|---------|------------|-------|------------|
| Product Name              | Volume Solids % | Weight Solids % | Density |            | VOC   |            |
|                           |                 |                 | g/mL    | lbs/US gal | g/L   | lbs/US gal |
| Infra-Red Primer Hardener | 33.9            | 39.9            | 0.986   | 8.23       | 593.1 | 4.95       |







| Properties  |
|---|
| <ul style="list-style-type: none"> <li>Promotes infra-red drying</li> </ul> |

| Substrates   |
|--|
| <ul style="list-style-type: none"> <li>Refer to the Technical Data Sheet for the base product</li> </ul> |



| Substrate Preparation   |  |
|---|--|
|  <b>All Substrates</b> | All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application. |

# Technical Data Sheet

## Product Preparation

|   |  |                              |  |
|---|--|------------------------------|--|
|  <b>Mixing Ratio</b><br>4:1 (by volume)  |  | <b>Concept<br/>2K Primer</b> | <b>Concept<br/>Infra-Red Primer<br/>Hardener</b> |
|   |  | 4 parts                      | 1 part   |
|  <b>Reducer</b>  | Refer to the Technical Data Sheet for the base product   |                              |  |
|  <b>Pot life</b><br>@ 25°C (77°F)  | Refer to the Technical Data Sheet for the base product   |                              |  |
|  <b>Spray viscosity</b><br>@ 25°C (77°F)   | Refer to the Technical Data Sheet for the base product   |                              |  |
|  <b>Product Application</b>   | Refer to the Technical Data Sheet for the base product   |                              |  |
|  <b>IR Drying</b>  | 5 minutes at half power at a distance of 80cm followed by 15 – 20 minutes at full power at a distance of 80cm. |                              |  |
| <p>This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.</p> |  |                              |  |

## Remarks

|   |  |
|---|--|
|  | Stir all products thoroughly each time before use.<br>Stir the mixture well after the weigh-out of the components. |
|  | Surface temperature must always be a minimum of 3°C (5°F) above dew point.   |

## Equipment Cleaning

Use recommended Concept Paints cleaner

## Dry Film Properties

After 7 days drying,  
when compared to similar technology products.

Refer to the Technical Data Sheet for the base product

# Technical Data Sheet

| Product Data         |  |
|----------------------|--|
| Colour               | Water white  |
| Theoretical Coverage | Refer to the Technical Data Sheet for the base product                     |
| Shelf Life           | 24 months in an unopened container at room temperature away from sunlight. |

| Product Packaging |                |                           |              |
|-------------------|----------------|---------------------------|--------------|
| Product Code 1    | Product Code 2 | Product Name              | Package Size |
| A04C/PRIMHINF     | 2569200        | Infra-Red Primer Hardener | 1L           |

| Safety   |
|--|
| <p>For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.</p> <p>Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.</p> |

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints  
26-30 Charles Street  
St Marys NSW 2760  
Sydney, Australia

ph. +61 (2) 9673 2555  
fax. +61 (2) 9623 1918  
info@conceptpaints.com.au  
www.conceptpaints.com.au