

Technical Data Sheet

Product Name	
Full Product Name	MS 100 2K Colour
Type of Product	2K acrylic urethane topcoat
Description	Concept MS-100 2K Colour is a 2K acrylic urethane topcoat, designed to give a significant reduction in the overall cost of a refinish job, whilst providing all of the characteristics of a good quality 2K product range. It is characterised by its excellent flow, coverage, high gloss finish, excellent chemical resistance and durability.

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
MS-100 2K Black (2:1)	38.0	44.6	0.982	8.19	543.8	4.54
MS-100 2K White (2:1)	43.7	59.5	1.213	10.12	491.5	4.10
MS Uni Hardener Slow	35.4	40.9	1.004	8.38	593.8	4.96
MS Uni Hardener Normal	33.3	39.9	0.986	8.23	593.1	4.95
MS Uni Hardener Fast	33.6	40.2	0.968	8.08	578.3	4.83
MS Uni Hardener Super Fast	31.5	38.9	0.938	7.83	572.7	4.78
2K Thinner Slow	0.0	0.0	0.893	7.45	892.7	7.45
2K Thinner	0.0	0.0	0.882	7.36	881.9	7.36
2K Thinner Fast	0.0	0.0	0.872	7.27	871.5	7.27

Properties
<ul style="list-style-type: none"> Economical to use
<ul style="list-style-type: none"> Excellent levelling and flow
<ul style="list-style-type: none"> High gloss and opacity

Substrates

- Concept MS-100 2K Primer - Grey
- Sound existing surfaces, except for unstable surfaces such as nitrocellulose or enamels.

Substrate Preparation



All Substrates

All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.

Product Preparation

	Mixing Ratio 2:1 (by volume)	Concept MS-100 2K Colour		Concept MS Uni Hardener	
		2 parts		1 part	
	Reducer	Up to 10% (v/v) of Concept 2K Thinner, if required.			
	Pot life @ 25°C (77°F)	4-5 hours			
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup	17-18 s		
		Ford 4 Cup	15-16 s		
	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
		Gravity feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		Suction feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		HVLP	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats	2-3	Apply one coat followed by one or two even full coats. Avoid heavy wet coats.		
	DFT Recommended	40-50 µm 1.6-2.0 mils			

Technical Data Sheet

Product Preparation cont

	Flash off time @ 25°C (77°F)	5-10 min between coats	
	Drying	Air Dry @ 25°C (77°F)	12-16 hours
		Low Bake @ 50°C (122°F)	20-30 min
<p>This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.</p>			

Remarks

	<p>Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.</p>
	<p>Surface temperature must always be a minimum of 3°C (5°F) above dew point.</p>

Equipment Cleaning

Use recommended Concept Paints 035 Gunwash
--

Dry Film Properties

	After 7 days drying, <u>when compared to similar technology products.</u>
Gloss	Excellent
Chemical resistance	Excellent
Durability	Excellent

Technical Data Sheet

Product Data	
Colour	White, Black
Theoretical Coverage	Approx. 6.0 m ² /L (245 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature, away from sunlight.

Product Packaging		
Product Code	Product Name	Package Size
AU4397000000X	MS 100 2K Black (2:1)	1L, 4L, 20L
AU4396000000X	MS 100 2K White (2:1)	1L, 4L, 20L
AU2139100000X	MS Uni Hardener Slow	500 mL, 1L
AU2139200000X	MS Uni Hardener Normal	500 mL, 1L
AU2139300000X	MS Uni Hardener Fast	500 mL, 1L
AU2139400000X	MS Uni Hardener Super Fast	500 mL, 1L
AU8319100000X	2K Thinner Slow	1L, 4L, 20L
AU8319200000X	2K Thinner	1L, 4L, 20L
AU8319300000X	2K Thinner Fast	1L, 4L, 20L

Safety
<p>For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.</p> <p>Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.</p>

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
office@conceptpaints.com.au
www.conceptpaints.com.au