

Technical Data Sheet

Product Name	
Full Product Name	MS 100 2K Primer Surfacer (Express)
Type of Product	2K urethane primer surfacer
Description	Concept MS 100 2K Primer Surfacer (Express) is a 2K urethane primer, characterized by optimum curing, sanding and excellent filling properties, fast drying as well as adhesion to most substrates.

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
MS 100 2K Primer Surfacer (Express)	47.9	68.9	1.469	12.26	457.4	3.82
Universal (MS) Hardener Slow	35.4	40.9	1.004	8.38	593.8	4.96
Universal (MS) Hardener Normal	33.9	39.9	0.986	8.23	593.1	4.95
Universal (MS) Hardener Fast	33.6	40.2	0.968	8.08	578.3	4.83
Universal (MS) Hardener Super Fast	31.5	38.9	0.938	7.83	572.7	4.78
2K Thinner Slow	0.0	0.0	0.893	7.45	892.7	7.45
2K Thinner	0.0	0.0	0.882	7.36	881.9	7.36
2K Thinner Fast	0.0	0.0	0.872	7.27	871.5	7.27

Properties
<ul style="list-style-type: none"> • High filling with excellent sag resistance
<ul style="list-style-type: none"> • Optimum through curing and drying
<ul style="list-style-type: none"> • Excellent adhesion
<ul style="list-style-type: none"> • Easy to sand with reduced paper clogging

Substrates

- Steel surfaces primed with Concept 1K Etch Primer or Concept Metal Etch Grey
- Aluminium surfaces primed with Concept 1K Etch Primer or Concept Metal Etch Grey
- Polyester spray filler
- Glass reinforced polyester (GRP & general types of fibreglass body parts)
- Sound, cured, cleaned and sanded existing surfaces

Substrate Preparation



All Substrates

All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application. Lightly rusted surfaces must be treated with Concept Light Rust & Metal Converter.

Product Preparation

	Mixing Ratio 4:1 (by volume)	Concept MS 100 2K Primer Surfacer (Express)		Concept Universal (MS) Hardener
		4 parts		1 part
	Reducer	Up to 10% (v/v) of Concept 2K Thinner, if required.		
	Pot life @ 25°C (77°F)	4-5 hours		
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	18-20 s 16-17 s	

Technical Data Sheet

Product Preparation cont

Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
	Gravity feed	1.8-2.0 mm 0.071-0.079"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
	Suction feed	1.8-2.0 mm 0.071-0.079"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
	HVLP	1.5-1.8 mm 0.059-0.071"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Airless Air Assisted Electrostatic	Consult the manufacturer's instructions.		
	Number of coats	2-3	Apply one coat followed by one or two even full coats. Avoid heavy wet coats.	
	DFT Recommended	50-80 µm 2.0-3.2 mils		
	Flash off time @ 25°C (77°F)	5 min between coats		
	Air Dry @ 25°C (77°F)	3-4 hours		
	Low Bake @ 50°C (122°F)	30-40 min		
	Sanding	Wet sand with P600-P800 before applying finish coat or Dry sand with P240 followed by P400-P500 using an orbital sander		
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.				

Remarks

	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints cleaner

Dry Film Properties

After 7 days drying,
when compared to similar technology products.

Hardness	Excellent
Flexibility	Excellent
Corrosion protection	Excellent
Durability	Excellent

Product Data

Colour	Grey
Theoretical Coverage	Approx. 5 m ² /L (205 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature away from sunlight.

Product Packaging

Product Code 1	Product Code 2	Product Name	Package Size
A03C/MS100PRIMG	1396200	MS 100 2K Primer Surfacer (Express)	4L
A04C/UNIMSS	2139100	Universal (MS) Hardener Slow	250 mL, 1L
A04C/UNIMSN	2139200	Universal (MS) Hardener Normal	250 mL, 1L
A04C/UNIMSF	2139300	Universal (MS) Hardener Fast	250 mL, 1L
A04C/UNIMSSF	2139400	Universal (MS) Hardener Super Fast	250 mL, 1L
A08C/2KTHS	8319100	2K Thinner Slow	1L, 4L, 20L
A08C/2KTHIN	8319200	2K Thinner	1L, 4L, 20L
A08C/2KTHF	8319300	2K Thinner Fast	1L, 4L, 20L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
info@conceptpaints.com.au
www.conceptpaints.com.au