

Technical Data Sheet

Version: 05

Product Name	
Full Product Name	No Mix Basecoat
Type of Product	Solvent borne clear over base (COB) basecoat
Description	Concept NO MIX Basecoat is a Clear Over Base (C.O.B) tinting system that requires no mixing machine. It delivers outstanding colour strength and depth, excellent flow characteristics, and superior colour matching accuracy.

Tinters

Code & Name of Tinter	Density g/mL	Weight Solids %	Volume Solids %	VOC g/L
NM-01 Black	1.018	36.4	29.1	647.3
NM-02 Blue	0.987	34.0	27.2	651.1
NM-03 Bright Blue	0.968	23.7	17.4	737.9
NM-04 Bright Gold	1.024	39.3	31.5	621.5
NM-05 Bright Red	0.983	28.4	21.5	703.4
NM-07 Copper	1.008	29.9	20.4	706.3
NM-08 Vivid Magenta	0.993	32.3	25.5	671.4
NM-09 Raven Black	0.926	15.9	12.2	779.0
NM-10 Deep Black	1.033	31.0	26.0	712.3
NM-11 Cobalt Blue	1.013	33.5	27.3	674.3
NM-12 Maroon	0.990	31.0	24.3	682.5
NM-13 Deep Maroon	0.995	32.6	25.8	671.1
NM-14 Garnet	0.999	34.3	27.5	656.2
NM-15 Green	1.044	36.3	28.8	664.4
NM-16 Green Blue	1.003	36.7	29.8	635.3
NM-17 Green Gold	1.041	34.5	28.7	681.4
NM-18 Grey Black	0.992	30.1	22.5	693.6
NM-19 Empress Black	0.912	16.5	11.0	763.8
NM-20 Light Red Oxide	1.030	31.2	20.7	708.0
NM-21 Lime	1.042	33.2	24.9	696.2

TDS - No Mix Basecoat page 1 of 7



Version: 05

Date: 14 April 2023

Technical Data Sheet

	1			
Tinters				
Code & Name of Tinter	Density g/mL	Weight Solids	Volume Solids %	VOC g/L
NM-22 Magenta	0.992	32.2	25.4	671.3
NM-23 Midnight Blue	1.012	37.0	29.1	638.2
NM-24 Red Gold	1.009	30.6	21.3	700.1
NM-25 Red Maroon	1.022	33.4	27.7	680.2
NM-26 Vivid Orange	0.999	35.2	28.5	647.9
NM-27 Ruby	0.920	21.1	14.5	726.1
NM-29 Midnight Black	1.030	38.0	32.9	641.5
NM-30 Violet	0.971	24.6	18.3	731.7
NM-31 White	1.173	45.4	28.6	640.5
NM-32 Yellow Gold	1.043	34.1	22.4	687.6
NM-33 Yellow Ochre	1.052	34.3	22.7	690.9
NM-34 Special Violet	1.008	30.2	24.4	704.1
NM-35 Port Wine Red	1.015	32.6	27.2	684.2
NM-36 Deep Blue	1.006	32.8	26.5	675.6
NM-37 Special Deep Black	0.975	23.0	17.4	751.8
NM-38 Special Red Maroon	1.005	31.4	25.3	689.0
NM-39 HS Special Red	1.003	33.3	25.9	669.2
NM-40 Royal Blue	0.988	32.7	26.3	664.9
NM-41 Reduced Black	0.967	24.5	18.0	730.6
NM-42 Silk Silver	1.035	30.5	19.1	719.4
NM-43 Silk Russet	1.038	30.5	18.9	721.5
NM-44 Silk Gold	1.031	30.2	19.0	719.9
NM-45 Silk Blue	1.028	29.2	18.1	727.3
NM-46 Silk Red	1.033	30.4	19.1	719.3
NM-47 Silk Green	1.035	30.6	19.2	718.3
NM-48 Silk Copper	1.030	29.8	18.7	723.2
NM-51 Red Yellow	1.005	33.2	26.3	671.0
NM-52 Topaz	1.008	33.7	25.5	668.3
NM-53 Organic Orange	0.998	31.7	23.2	681.2
NM-54 Special Silver Bright Fine	0.980	28.0	20.8	705.1
NM-55 Special Silver Coarse	0.997	33.4	25.8	664.5
NM-56 Silver Dollar Bright Coarse	0.999	33.3	25.4	666.5
NM-57 Silver Dollar Bright	0.999	33.2	25.3	667.5
NM-59 Metallic Additive	0.963	23.4	17.0	737.7
NM-60 Stabilizer Additive	0.963	23.4	17.0	737.7
NM-61 Effect White	1.091	38.4	27.5	671.8
NM-62 HS Special White	1.286	52.0	31.0	616.9
NM-63 HS Special Yellow	1.185	45.2	28.0	649.8

TDS - No Mix Basecoat page 2 of 7



Technical Data Sheet

Version: 05

Tinters]			
Code & Name of Tinter	Density g/mL	Weight Solids %	Volume Solids %	VOC g/L
NM-65 Fine Metallic	0.980	24.3	16.2	742.5
NM-68 Extra Fine Silver NM-69 Fine Silver NM-70 Silver NM-71 Medium Silver NM-72 Coarse Silver NM-74 Coarse Aluminium NM-75 Extra Coarse Aluminium NM-75 Extra Coarse Aluminium NM-77 Fine White Pearl NM-80 Yellow Pearl NM-80 Yellow Pearl NM-82 Fine Yellow Gold Pearl NM-83 Orange Pearl NM-87 Bright Russet Pearl NM-87 Bright Russet Pearl NM-88 Fine Russet Pearl NM-89 Blue Russet Pearl NM-90 Red Blue Pearl NM-91 Fine Blue Pearl NM-92 Green Blue Pearl NM-95 Blue Green Pearl NM-95 Fine Green Pearl NM-96 Red Pearl NM-97 Fine Silver Pearl NM-98 Fine Violet Pearl NM-99 Metallic Raiser NM-101 Red Candy NM-102 Brandy Wine Candy NM-103 Yellow Candy	0.974 0.977 0.972 0.981 0.977 0.974 0.979 1.048 1.040 1.055 1.024 0.990 1.048 1.056 1.057 1.048 1.049 1.047 1.033 1.045 1.045 1.046 1.035 1.046 1.035 1.064 1.014 1.029 1.062	23.6 23.9 23.5 24.3 23.8 23.6 24.5 32.3 31.7 33.0 30.3 26.7 32.2 32.8 32.8 32.2 32.0 32.0 30.9 31.9 32.3 32.3 31.0 33.8 30.3 16.9 18.7	16.2 15.9 16.1 16.0 16.1 16.4 20.2 20.1 20.6 19.1 18.0 20.2 20.2 20.1 20.1 19.8 19.9 19.7 20.0 20.2 20.2 20.3 19.7 20.8 20.5 14.0 16.0	744.0 743.9 743.8 742.8 744.7 743.8 739.2 709.4 710.2 706.0 713.6 726.2 709.7 709.4 710.3 710.8 713.4 712.1 714.4 711.6 709.4 709.0 713.8 704.3 706.1 855.6 864.2
NM-104 Green Candy	1.075 1.067	20.4	17.8 17.6	855.8 849.0
MS Uni Hardener Fast MS Uni Hardener Normal MS Uni Hardener Slow MS Uni Hardener Super Fast NM Reducer	0.968 0.986 1.004 0.938 0.883	40.2 39.9 40.9 38.9 0.0	33.6 33.9 35.4 31.5 0.0	578.3 593.1 593.8 572.7 8.83

TDS - No Mix Basecoat page 3 of 7



Technical Data Sheet

Version: 05

Properties

- Superior pigment distribution, eliminating mottling
- Improved colour depth, providing better coverage
- Consistency in Tinter/Toner strength, assisting with colour matching
- Greater flow characteristics resulting in ease of application
- Incorporating an extensive range of colour formulations

Substrates

- Concept Paints Primers and primer surfacers e.g. HS 2K Primer
- Sound existing surfaces, except for unstable surfaces such as nitrocellulose or enamels

Substrate Preparation



All Substrates

All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application

TDS - No Mix Basecoat page 4 of 7



Technical Data Sheet

Version: 05

Product Preparation	1
----------------------------	---

	Reducer	1:1 (100% (v/v) of Concept NM Reducer			
		Note: To activate, 5% Concept MS Uni Hardener can be added to the No Mix colour, before thinning, if required			
A B	Pot life @ 25°C (77°F)	N/A			
S	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	17-18 s 15-16 s		
	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
>1 / 1	oquipmoni	Gravity feed	1.3-1.4 mm 0.051-0.055"	190-200 kPa 1.9-2.0 bar 27.5-29 psi	15-20 cm 6-8 inch
****		Suction feed	1.3-1.4 mm 0.051-0.055"	190-200 kPa 1.9-2.0 bar 27.5-29 psi	15-20 cm 6-8 inch
HVLP		HVLP	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats / DFT	2-3 coats	20-25 µm 0.8-1.0 mils		
<u> </u>	Flash off time @ 25°C (77°F)	5-10 min between coats			
	Drying	Air Dry	Air Dry 30-40 min @ 25°C (77°F)		

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

TDS - No Mix Basecoat page 5 of 7



Technical Data Sheet

Version: 05

Remarks	
	5 – 10% v/v of Concept NM-99 Metallic Raiser may be added for a brighter, cleaner and a more brilliant face and flip, if required.
	Shake all Tinter/Toners thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
oF/°C	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints 035 Gunwash

Product Data	
Theoretical Coverage	Approx. 6-8 m ² /L DFT(after thinning)
Shelf Life	36 months in an unopened container at room temperature away from sunlight.

TDS - No Mix Basecoat page 6 of 7



Technical Data Sheet

Version: 05

Product Packaging

48 x Concept No Mix Solid and Reduced Tinters	250mL, 1L
7 x Concept No Mix Xirallic Tinters	250mL, 1L
14 x Concept No Mix Metallic Tinters	1L
17 x Concept No Mix Pearl Tinters	1L
1 x Concept No Mix Metallic Raiser Tinter (NM-99)	1L
4 x Concept No Mix Candy Tinters	250mL
Concept MS Uni Hardeners	500mL, 1L
Concept NM Reducer	1L, 4L, 20L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints 26-30 Charles Street St Marys NSW 2760 Sydney, Australia ph. +61 (2) 9673 2555 fax. +61 (2) 9623 1918 office@conceptpaints.com.au www.conceptpaints.com.au

TDS - No Mix Basecoat page 7 of 7