

2K Matt Clear (2:1)

2K Acrylic Urethane Clearcoat

Date: 21st October 2016 Version:01

Product Name	
Full Product Name	2K Matt Clear (2:1)
Type of Product	2K acrylic urethane clearcoat
Description	Spray Chief 2K Matt Clear (2:1) is a high performance 2K clearcoat, designed specifically to give a matt finish (10%), replicating the latest OEM designs. It is characterised by its superior flow, exceptional chemical resistance and hardness.

Products						
Product Name	Volume Solids %	Weight Solids %	Den g/mL lb	sity os/US gal	VC g/L lb	os/US gal
2K Matt Clear (2:1)	50.1	57.3	1.069	8.92	547.5	4.57
2:1 MS Hardener	33.9	39.9	0.986	8.23	593.1	4.95
2K Thinner	0.0	0.0	0.882	7.36	881.9	7.36

Properties

- Excellent flow
- Matt finish

Substrates

- Spray Chief range of basecoat systems, including: Candy Apple, Candy Pearl, Candy Apple Rainbow Finish, Black Pearl, Fluro, Clear Pearl and Shim'r
- Spray Chief range of 2:1 systems, including: Candy Apple (2:1), Candy Apple (2:1) Rainbow Finish, Black Pearl (2:1) and Fluro (2:1).



2K Matt Clear (2:1)

2K Acrylic Urethane Clearcoat

Date: 21st October 2016 Version:01

Substrate Preparation	
All Substrates	All surfaces must be clean and free from any contamination prior to application.

Prod	luct Preparati	ion			
	Mixing Ratio 2:1 (by volume)	•	y Chief Clear (2:1)	Spray Chief 2:1 MS Hardener	
		2	parts	1	oart
	Reducer	Up to 10% (v/v) of Spray Chief 2K Thinner, if required			
A B	Pot life @ 25°C (77°F)	2-3 hours			
S	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	•		
	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
≥1		Gravity feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
*		Suction feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
HVI P			1 2-1 3 mm	40-70 kPa	15-20 cm

1.2-1.3 mm

0.047-0.051"

coats.

5-10 min between coats, or until touch dry

HVLP

2-3

50-60 μm

2.0-2.4 mils

TDS SC	03 – 2K	Matt	Clear	(2:1)

Number of

Recommended

Flash off time

@ 25°C (77°F)

coats

DFT

HVLP

15-20 cm

6-8 inch

0.4-0.7 bar

Apply two to three even full coats. Avoid heavy wet



2K Matt Clear (2:1)

2K Acrylic Urethane Clearcoat

Date: 21st October 2016 Version:01

Product Preparation cont

Drying Air Dry @ 25°C (77°		16-24 hours
	Low Bake @ 50°C (122°F)	30-40 min

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Remarks	
	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
oF / oC	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Spray Chief cleaner

Dry Film Properties	After 7 days drying, when compared to similar technology products.
Gloss @ 60°	10-12 GU
Hardness	Excellent
Chemical resistance	Excellent



2K Matt Clear (2:1)

2K Acrylic Urethane Clearcoat

Date: 21st October 2016 Version:01

Product Data	
Colour	Semi-transparent
Theoretical Coverage	Approx. 7 m ² /L (285 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature away from sunlight.

Product Packaging			
Product Code 1	Product Code 2	Product Name	Package Size
A16/2KMATTCLR A16/2:1HARDMS A16/2KTHIN	8889001 8899200 8949200	2K Matt Clear (2:1) 2:1 MS Hardener 2K Thinner	1.5L (Kit), 6L (Kit) 500mL, 1L 1L, 4L, 20L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations



2K Matt Clear (2:1)

2K Acrylic Urethane Clearcoat

Date: 21st October 2016 Version:01

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Chilmix Pty Limited t/a Spray Chief Custom Paints ABN 28 069 967 362 26-30 Charles Street, St Marys NSW 2760 Sydney, Australia ph. +61 (2) 9673 2555 fax. +61 (2) 9623 1918 sales@spraychiefcustompaints.com.au www.spraychiefcustompaints.com.au