











Product Name	
Full Product Name	Super gloss clear (aerosol)
Type of Product	Iso-Free Clearcoat
Description	Concept Super gloss clear (aerosol) is a “blocked” 2K isocyanate free (moister cured), high quality clearcoat, suitable for all metallic based and acrylic automotive paints. It is characterised by exceptionally high gloss, excellent durability and adhesion. It is ideal for spot repairs and small areas.

Properties	
<ul style="list-style-type: none"> • High gloss 	
<ul style="list-style-type: none"> • Excellent adhesion 	
<ul style="list-style-type: none"> • Excellent durability 	
<ul style="list-style-type: none"> • Ready for use (aerosol) 	


Substrates	
<ul style="list-style-type: none"> • Concept No Mix Basecoats 	
<ul style="list-style-type: none"> • Concept UniCryl 3000 acrylic paint systems 	

Substrate Preparation	
 All Substrates	<p>Ensure that all surfaces are clean and free from any contamination prior to application. Mask off surrounding areas to avoid overspray.</p>


Product Preparation

	Shake can	Invert and shake the can thoroughly, until the agitation ball can be heard (two to three minutes). Continue to shake the can during application.	
	Pot life @ 25°C (77°F)	N/A	
	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	N/A
	Application	Spray in an even overlapping pattern from a distance of approx. 25 cm.	
	Number of coats	2-3	Apply two to three even coats to gradually increase film thickness. Avoid heavy wet coats to minimise risk of runs.
	DFT Recommended	25 µm 1.0 mil	
	Flash off time @ 25°C (77°F)	5 min between coats	
	Drying	Air Dry @ 25°C (77°F)	24 hours – Full cure
	Polishing (Optional)	Sand with P1200 abrasive prior to polishing	
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.			

Remarks

	Surface temperature must always be a minimum of 3°C (5°F) above dew point.
---	--

Equipment Cleaning

	Turn the can upside down and spray until the jet clears. Any over spray maybe cleaned up with Mineral Turps
---	---

Technical Data Sheet

Dry Film Properties	After 7 days drying, <u>when compared to similar technology products.</u>
Adhesion	Excellent
Gloss	Excellent
Durability	Excellent

Product Data	
Colour	Water white
Theoretical Coverage	Approx. 3.0 m ² (120 ft ²)/400g @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature away from sunlight.

Product Packaging			
Product Code 1	Product Code 2	Product Name	Package Size
A07C/2KCLR/400G		Super gloss clear (aerosol)	400g (aerosol)

Safety
Before using, read and follow all label and Safety Data Sheet (SDS) precautions, including respiratory protection and other Personal Protective Equipment such as safety clothing, glasses and gloves. Use only in a well-ventilated area.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
info@conceptpaints.com.au
www.conceptpaints.com.au