

Technical Data Sheet

Version:02

Product Name	
Full Product Name	Two in One Primer - Beige
Type of Product	1K acrylic high build primer filler
Description	Concept Two in One Primer - Beige as its name suggests, is two systems in one: 1K primer and a putty. A high build acrylic based product, its unique formulation ensures that there is no need to apply a putty and a primer over the prepared surface. Two in One Primer is the only product required before topcoat.

Products				
Product Name	Volume Solids %	Weight Solids %	Density g/mL lbs/US gal	VOC g/L lbs/US gal
Two in One Primer - Beige	29.8	51.0	1.209 10.09	592.7 4.95
808 Multi Thinner	0.0	0.0	0.805 6.71	803.5 6.71

Properties

- High build
- Two in one (primer and a putty)
- Easy to sand

Substrates

- Mild steel surfaces primed with Concept 103 Etch Primer or Concept 110 Metal Etch -Grey
- Aluminium, primed with Concept 103 Etch Primer or Concept 110 Metal Etch Grey
- Stainless steel grade 316 primed with Concept 103 Etch Primer or Concept 110 Metal Etch Grey
- Galvanised steel, Zincalume, Zincanneal primed with Concept 103 Etch Primer or Concept 110 Metal Etch - Grey
- Glass reinforced polyester (GRP & general types of fibreglass body parts)
- Sound existing coatings



Technical Data Sheet

Version:02

Substrate Preparation	
All Substrates	All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application. Lightly rusted surfaces must be treated with Concept 025 Rust Converter.

Product Preparation

	Reducer	50% (v/v) of Concept 808 Multi Thinner.			
A B	Pot life @ 25°C (77°F)	N/A			
S	Spray viscosity @ 25°C (77°F)	BSB 4 Cup Ford 4 Cup	20-23 s 17-20 s		
	Spray equipment	Gun type	Fluid tip	Spray pressure	Spray Distance
≥1 / 1		Gravity feed	1.4-1.8 mm 0.055-0.071"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
>77		Suction feed	1.4-1.8 mm 0.055-0.071"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
HVLP		HVLP	1.5-1.8 mm 0.059-0.071"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	Number of coats	2-3 Apply one coat followed by one or two even full coats. Avoid heavy wet coats.			
	DFT Recommended	50-80 µm 2.0-3.2 mils			
? ↑ ? ↑ ?	Flash off time @ 25°C (77°F)	5 min between coats			
	Drying	Air Dry @ 25°C (77°F) 40-60 min			
	Sanding	Wet sand with P600-P800 before applying finish coat, or Dry sand with P240 followed by P400-P500 using an orbital sander			

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.



Technical Data Sheet

Version:02

Remarks	
	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
°F/°C	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning

Use recommended Concept Paints 035 Gunwash

Dry Film Properties	After 7 days drying, when compared to similar technology products.	
Adhesion	Excellent	
Corrosion protection	Excellent	
Sanding	Excellent	

Product Data		
Colour	Beige	
Theoretical Coverage	Approx. 3.5 m ² /L (145 ft ² /US gal) @ recommended DFT	
Shelf Life	36 months in an unopened container at room temperature away from sunlight.	

Product Packaging		
Product Code	Product Name	Package Size
AU1076100000X AU8089200000X	Two in One Primer - Beige 808 Multi Thinner	1L, 4L, 20L 1L, 4L, 20L



Technical Data Sheet

Version:02

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints 26-30 Charles Street St Marys NSW 2760 Sydney, Australia ph. +61 (2) 9673 2555 fax. +61 (2) 9623 1918 office@conceptpaints.com.au www.conceptpaints.com.au