

Technical Data Sheet

Product Name

Full Product Name	MS Uni Hardener
Type of Product	Isocyanate hardener
Description	MS Uni Hardener's are a range of isocyanate hardeners, specifically designed for use with polyurethane 2K paints. There are four (4) hardeners in the range to give the best performance of the products in varying conditions. By following the chart in the "Selection Guide", choosing the correct hardener is easy.

Products

Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
MS Uni Hardener Slow	31.5	38.9	0.938	7.83	572.7	4.78
MS Uni Hardener Normal	33.6	40.2	0.968	8.08	578.3	4.83
MS Uni Hardener Fast	33.9	39.9	0.986	8.23	593.1	4.95
MS Uni Hardener Super Fast	35.4	40.9	1.004	8.38	593.8	4.96

Properties

- Refer to the Technical Data Sheet of the base product.

Substrates

- Refer to the Technical Data Sheet for the base product

Substrate Preparation

	All Substrates	All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.
--	-----------------------	--

Technical Data Sheet

Product Preparation

	Mixing Ratio 2:1 (by volume)	Concept 2K Product(s)	Concept MS Uni Hardener
		2 parts	1 part
	Reducer	Refer to the Technical Data Sheet for the base product	
	Pot life @ 25°C (77°F)	Refer to the Technical Data Sheet for the base product	
	Spray viscosity @ 25°C (77°F)	Refer to the Technical Data Sheet for the base product	
	Product Application	Refer to the Technical Data Sheet for the base product	
<p>This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.</p>			

Selection Guide

Low Temperature Baking									
Baking Temperature		25°C	30°C	35°C	40°C	45°C	50°C	55°C	60°C
		77°F	86°F	95°F	104°F	113°F	122°F	131°F	140°F
Universal (MS) Hardener	Super Fast	[Progress bar]							
	Fast	[Progress bar]							
	Fast	[Progress bar]							
	Normal	[Progress bar]							
	Slow	[Progress bar]							
				40 min				35 min	
Air Drying									
Ambient Temperature		10°C	15°C	20°C	25°C	30°C	35°C	40°C	45°C
		50°F	59°F	68°F	77°F	86°F	95°F	104°F	113°F
Universal (MS) Hardener	Super Fast	[Progress bar]							
	Fast	[Progress bar]							
	Fast	[Progress bar]							
	Normal	[Progress bar]							
	Slow	[Progress bar]							
Note: Ensure that substrate temperature is at least 3°C (5°F) above Dew Point Temperature.									

Technical Data Sheet

Remarks



Stir all products thoroughly each time before use.
Stir the mixture well after the weigh-out of the components.



Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Important Note:

This Hardener Selection Guide is issued by Concept Paints as a guidance only and is current and correct to the best of our knowledge at the time of issuance intended. It is recommended for use by professional trade and industrial applicators with Concept Paints products only. When using with other company's product, adjustments may be required.

The user must ensure suitability of the products and their performance for the application at hand. Concept Paints assumes no responsibility nor provides any warranty.

Equipment Cleaning

Use recommended Concept Paints 035 Gunwash

Dry Film Properties

After 7 days drying,
when compared to similar technology products.

- Refer to the Technical Data Sheet for the base product.

Product Data

Colour	Water white
Theoretical Coverage	Refer to the Technical Data Sheet for the base product
Shelf Life	24 months in an unopened container at room temperature away from sunlight.

Technical Data Sheet

Product Packaging

Product Code	Product Name	Package Size
AU2139100000X	MS Uni Hardener Slow	500mL, 1L
AU2139200000X	MS Uni Normal Hardener	500mL, 1L
AU2139300000X	MS Uni Hardener Fast	500mL, 1L
AU2139400000X	MS Uni Hardener Super Fast	500mL, 1L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
office@conceptpaints.com.au
www.conceptpaints.com.au